

S6 1 PN='DE 2347013'
? t6/7/1

6/7/1
DIALOG(R)File 350:Derwent WPIX
(c) 2003 Thomson Derwent. All rts. reserv.

001373086

WPI Acc No: 1975-22724W/197514

Polyester or copolyester granulate precrystallised in hot liq. - esp.
water without agitation thus reducing energy consumption
Patent Assignee: K FISCHER APP ROHRLEITUN (FISK)

Number of Countries: 001 Number of Patents: 001

Patent Family:

Patent No	Kind	Date	Applicat No	Kind	Date	Week
DE 2347013	A	19750327				
					197514	B

Priority Applications (No Type Date): DE 2347013 A 19730914

Abstract (Basic): DE 2347013 A

A method of making dry polyester or copolyester granulate, by pre-crystallisation, then drying, of fragmented, amorphous polycondensate is as follow: the pre-crystallisation is effected within a liq. heat vehicle at 80-110 (85-95)degrees C in a granulate; mixt. ratio of up to 1:1 then the liq. is removed and the granulate is gas-dried. The energetic agitation required for particles which are pre-crystallised in gas is not necessary.

Derwent Class: A23

International Patent Class (Additional): B29B-001/02